

Allfasteners Pty Ltd
78-84 Logistics Street
Keilor Park 3042 Melbourne
Victoria AUSTRALIA

Eurofins Product Testing A/S
Smedeskovvej 38
8464 Galten
Denmark

CustomerSupport@eurofins.com
www.eurofins.com/VOC-testing

VOC TEST REPORT

VOC Content

1 September 2020

1 Sample Information

Sample name	FIX 360 - Grey
Sample no.	392-2020-00330401
Production date	29/05/2020
Batch No.	2050905
Sample reception	03/08/2020

2 Brief Evaluation of the Results

Regulation or protocol	Conclusion	Version of regulation or protocol
SCAQMD Rule 1168	Pass	October 2017
LEED v4.1 (VOC Content)	Pass	

Full details based on the testing and direct comparison with limit values are available in the following pages



Janne Rothmann Norup
Analytical Service Manager

3 Applied Test Methods

3.1 General Test References

Regulation, protocol or standard	Scope	Version
CARB 2007 SCM	Architectural coatings	February 2008
SCAQMD Rule 1168	Adhesive and sealant applications	October 2017

3.2 Specific Laboratory Sampling and Analyses

Test	Regulation, protocol or standard	Version	Internal SOP	Limit of detection [g/L]	Uncertainty Um _a %
VOC	ASTM D2369	2010	71 M 544830	1	10

3.3 Preparation of the Test Specimen

The sample was homogenised and applied directly onto the test dish.

4 Results

	Remarks on the test results	Results	Unit
Density *	Supplied by the Customer	1.60	g/mL
Water Content *	Supplied by the Customer	0.551	g/L
Exempt compounds *	Assumed to be 0	0	% (w/w)
Solids Content	Tested by the lab	99.2	% (w/w)
VOC content (less water)	Calculated based on the results above	12	g/L
VOC content (less water)	Calculated based on the results above	0.77	% (w/w)

4.1 Comparison with Limit Values of VOC Content (less Water)

Parameter	Results [g/L]	Product type	Regulation or protocol	VOC limit [g/L]
VOC content	12	Drywall and panel adhesive	SCAQMD Rule 1168	50

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

5 Appendices

5.1 How to Understand the Results

5.1.1 Acronyms Used in the Report

- < Means less than
- > Means bigger than
- * Not a part of our accreditation
- ⊠ Please see section regarding uncertainty in the Appendices
- 1 Analysed by another Eurofins laboratory

5.2 Description of VOC Content Test

5.2.1 Testing of VOC

Volatile content of the sample was determined gravimetrically by heating to 110 °C in 60 minutes. Multicomponent products are mixed according to the manufacturer's instructions and allowed to cure before heating.

The result is the average of two replicates. The result was calculated as:

$$VOC = \frac{([g \text{ All Volatiles}] - [g \text{ Water}] - [g \text{ Exempt Compounds}])}{([liter \text{ Material}] - [liter \text{ Water}] - [liter \text{ Exempt Compounds}])}$$

5.3 Uncertainty of the Test Method

Um(%): The expanded uncertainty Um is equal to 2 x RSD%.